









Product properties										
Format [mm]	Trendtime 1	Trendtime 3	Trendtime 4	Trendtime 6	Trendtime 8	Trendtime 9				
	2010 x 130 x 13	570 x 95 x 10,5	2010 x 160 x 13	2200 x 185 x 13	1882*x 190 x 15	Basket weave	Strip mix	Mini checkerboard	Old Block pattern	Checkerboard
Top layer:	ca. 3,6 mm	ca. 2,5 mm	ca. 3,6 mm	ca. 3,6 mm	ca. 4 mm	ca. 3,6 mm	ca. 3,6 mm	ca. 3,6 mm	ca. 3,6 mm	ca. 3,6 mm
Packaging Pack: m ² /kg	9 Elements 2,352 / 17,1	20 Elements 1,083 / 5,40	9 Elements 2,894 / 19,40	9 Elements 3,663 / 29,304	8 Elements 2,861 / 26,40	8 Elements 3,089 / 23,56	8 Elements 3,256 / 24,832	8 Elements 3,22 / 24,6	8 Elements 3,784 / 28,864	8 Elements 2,827 / 24,6
Pallet: m ² /kg	40 Packs 94,07 / 684,00	36 Packs 38,99 / 194,40	32 Packs 92,621 / 620,64	32 Packs 117,22 / 937,73	32 Packs 91,55 / 844,80	32 Packs 98,842 / 753,92	32 Packs 104,192 / 794,624	32 Packs 103,055 / 787,2	32 Packs 121,088 / 923,648	32 Packs 90,458 / 787,2
Warranty	25 years					Notes				
*	Other formats possible. One short-length per packet possible					- cleaning an maintenance see instructions - technical changes reserved				

Product labelling					Tolerances (EN 13489)			
      					Only lacquered products:		Admissible difference in length (± 0.1 %)	± 0,05 %
					Admissible difference in width (± 0.2 mm)	± 0,1 mm		
					Squareness of the element (≤ 0.1 %)		≤ 0,05 %	
					Longitudinal curvature along the element (≤ 0.1 %)		≤ 0,05 %	
					Transverse curvature across the width (≤ 0.1 %)		≤ 0,08 %	
					Height differences of elements (≤ 0.2 mm)		≤ 0,18 mm	
					Moisture content at the time of first delivery (5-9%)		6 – 8 %	

Classification general product features											
		Test method	Rating								
	Resistance to roller castor chairs	EN 425	We recommend the use of a conventional chairmat								
	Effect of a furniture leg	EN 424	No visible changes								
	Thermal resistance Suitable for installation over underfloor heating when using an appropriate underlay and moisture barrier.	EN 12664	<table border="1"> <tr> <td>Trendtime 1 / 4 / 6</td> <td>0,087 m²K/W</td> </tr> <tr> <td>Trendtime 3</td> <td>0,070 m²K/W</td> </tr> <tr> <td>Trendtime 8</td> <td>0,1 m²K/W</td> </tr> <tr> <td>Trendtime 9</td> <td>0,093 m²K/W</td> </tr> </table>	Trendtime 1 / 4 / 6	0,087 m ² K/W	Trendtime 3	0,070 m ² K/W	Trendtime 8	0,1 m ² K/W	Trendtime 9	0,093 m ² K/W
Trendtime 1 / 4 / 6	0,087 m ² K/W										
Trendtime 3	0,070 m ² K/W										
Trendtime 8	0,1 m ² K/W										
Trendtime 9	0,093 m ² K/W										
	Formaldehyde (E1 = 0.1 ppm)	EN 717-1	≤ 0,05 ppm								
	Acoustical - Impact noise reduction	ISO 717-2	<table border="1"> <tr> <td>Trendtime 1 / 4 / 6 / 8 / 9</td> <td>18 dB (with Akustik-Protect 100)</td> </tr> <tr> <td>Trendtime 3</td> <td>22 dB (with Akustik-Protect 100)</td> </tr> </table>	Trendtime 1 / 4 / 6 / 8 / 9	18 dB (with Akustik-Protect 100)	Trendtime 3	22 dB (with Akustik-Protect 100)				
Trendtime 1 / 4 / 6 / 8 / 9	18 dB (with Akustik-Protect 100)										
Trendtime 3	22 dB (with Akustik-Protect 100)										
	Resistance to roller castor chairs	Private waste disposal with normal household waste / bulky waste possible									

Classification surface characteristics					
		Test method	Rating		
			Natural oiled	Natural oiled (rough sawn)	Lacquer
	Slip resistance	EN 13893	μ ≥ 0,47	μ ≥ 0,47	μ ≥ 0,47
		CEN/TS 15676	46 SRT (SRV wet) 103 SRT (SRV dry)	57 SRT (SRV wet) 99 SRT (SRV dry)	29 SRT (SRV wet) 51 SRT (SRV dry)
	Reaction to fire, click-installation as a floating floor	EN 13501-1	D _{fl} s1		
	Reaction to fire, installation by all-over adhesion	EN 13501-1	D _{fl} s1		
	Chemical resistance	EN 13442	Category 4	Category 4	Category 5
	Bond strength / Cross cutting test	ISO 2409	n.n.	n.n.	Category 0
	Slip resistance, inclined plane	DIN 51130	R 10	R 13	R 9

Changed:	QMB	File name:	20170116_PA_TDS_Parkett_Trendtime_EN
Date:	01.05.2013	Update:	www.parador.eu/service/catalogues-downloads/technical-data-sheets
Our technical data sheets are constantly updated and adapted to the latest technology. This version replaces all earlier versions and is valid from:			16.01.2017

Free sorting according to EN 13489			
Assortment:	Wide plank		
Characteristics according to EN 1310:	Upper side of the floor board		
Design:	Trendtime 1		Trendtime 3
Type of wood:	Bamboo	Oak	Oak
Botanical designation / Code (EN 13556):	Phyllostachys pubescens	Quercus petraea Liebl., Quercus robur L. / QCXE	Quercus petraea Liebl., Quercus robur L. / QCXE
Origin:	CN	DE, AT, HU, HR, SK, BA, UA, FR, CZ	DE, AT, HU, HR, SK, BA, UA, FR, CZ
Shortcut / sorting / date (internal):	ER-TT1-BAM	ER-TT1-EI	ER-TT3-EI
	Version 1 2011	Version 5 2011	Version 2 2012
	N2	N2	A3
Grade:	Nature	Select	Living
Sound sapwood	-	not permitted	permitted
Knot (intergrown)	-	permitted: up to 15 mm	permitted: up to 30 mm
Falling out knot	-	not permitted	permitted: up to 10 mm
Pinkknots	-	permitted: cluster of knots	permitted
Filling	permitted	permitted	permitted
Slight cracks / hairline cracks	not permitted	permitted	permitted: up to 1x100 mm
Sugar inclusions, mineral inclusions	-	-	-
Bark pocket	not permitted	not permitted	not permitted
Lightning cracks	-	permitted	permitted
Slope of grain	no criterion	no criterion	no criterion
Healthy heart	-	not permitted	-
Medullary ray	-	permitted	permitted
Discoloration, colour variation	permitted	permitted: all colours	permitted: all colours
White streaks	permitted	permitted	permitted
Pilling sticks marking	not permitted	not permitted	not permitted
Biodeterioration (EN 1311)	not permitted	not permitted	not permitted
Non-visible parts			
All features without restrictions to size or quantity permitted, provided they do not affect the strength or durability of the floor.			
Comment			
Maximum 3% of floor board are allowed in the next lower grading. Wood is a natural product and therefore different in colour and texture. Samples, brochures and photos are therefore only approximate and not binding. The action of sunlight affects the natural variation in wood shade. This allows the product present at the time of delivery of significant differences to master.			

Changed:	QMB	File name:	20170116_PA_TDS_Parkett_Trendtime_Anhang_EN
Date:	01.03.2013	Update:	www.parador.eu/service/catalogues-downloads/technical-data-sheets
Our technical data sheets are constantly updated and adapted to the latest technology. This version replaces all earlier versions and is valid from:			16.01.2017
			Page 1 of 4

Free sorting according to EN 13489					
Assortment:	Wide plank				
Characteristics according to EN 1310:	Upper side of the floor board				
Design:	Trendtime 4				
Type of wood:	Oak	American cherry	American walnut		
Botanical designation / Code (EN 13556):	Quercus petraea Liebl., Quercus robur L. / QCXE	Prunus serotina Ehrh. / PRSR	Juglans nigra L. / JGNG		
Origin:	DE, AT, HU, HR, SK, BA, UA, FR, CZ	CA, US	US		
Shortcut / sorting / date (internal):	ES-LH-TT4-EI		ER-TT4-KIR ami.	ER-TT4-SWN	
	Version 12 2016	Version 5 2016	Version 2 2012	Version 4 2013	
	N4	N6	N2	N2	N4
Grade:	Living	Rustique	Nature	Nature	Living
Sound sapwood	permitted	not permitted	permitted	permitted	permitted
Knot (intergrown)	permitted: up to 40 mm	permitted: up to 80 mm	permitted	permitted: up to 15 mm	permitted
Falling out knot	permitted: up to 25 mm	permitted: up to 40 mm	permitted: up to 10 mm	permitted: up to 10 mm	permitted: up to 25 mm
Pinkknots	permitted: Cluster of knots	permitted: Cluster of knots	permitted	permitted	permitted
Filling	permitted	permitted	permitted	permitted	permitted
Slight cracks / hairline cracks	permitted: up to 1 x 200mm	permitted	not permitted	not permitted	not permitted
Sugar inclusions, mineral inclusions	-	-	permitted	-	-
Bark pocket	not permitted	permitted	not permitted	not permitted	not permitted
Lightning cracks	permitted: in knots	permitted	not permitted	-	permitted: in knots
Slope of grain	no criterion	no criterion	no criterion	no criterion	no criterion
Healthy heart	not permitted	permitted	-	-	-
Medullary ray	permitted	permitted	permitted	-	-
Discoloration, colour variation	permitted: slight colour variations / slight discolourations	permitted: all colours variations / slight discolourations	permitted: all colours	permitted: all colours	permitted: all colours
White streaks	-	permitted	-	-	-
Pilling sticks marking	not permitted	not permitted	not permitted	not permitted	not permitted
Biodeterioration (EN 1311)	not permitted	not permitted	not permitted	not permitted	not permitted
Non-visible parts					
All features without restrictions to size or quantity permitted, provided they do not affect the strength or durability of the floor.					
Comment					
Maximum 3% of floor board are allowed in the next lower grading. Wood is a natural product and therefore different in colour and texture. Samples, brochures and photos are therefore only approximate and not binding. The action of sunlight affects the natural variation in wood shade. This allows the product present at the time of delivery of significant differences to master.					

Changed:	QMB	File name:	20170116_PA_TDS_Parkett_Trendtime_Anhang_EN		
Date:	01.03.2013	Update:	www.parador.eu/service/catalogues-downloads/technical-data-sheets		
Our technical data sheets are constantly updated and adapted to the latest technology. This version replaces all earlier versions and is valid from:			16.01.2017	Page 2 of 4	

Free sorting according to EN 13489			
Assortment:	Wide plank		
Characteristics according to EN 1310:	Upper side of the floor board		
Design:	Trendtime 6		Trendtime 8
Type of wood:	Oak	Oak	
Botanical designation / Code (EN 13556):	Quercus petraea Liebl., Quercus robur L. / QCXE		Quercus spp. / QCXE
Origin:	DE, AT, HU, HR, SK, BA, UA, FR, CZ		FR
Shortcut / sorting / date (internal):	ER-LH-EI	ER-LH-EI	ER-TT8-EI
	Version 6 2016		Version 4 2015
	N3	N4	N8
Grade:	Nature	Living	Classic
Sound sapwood	not permitted	permitted	permitted
Knot (intergrown)	permitted: up to 30 mm	permitted: up to 50 mm	permitted
Falling out knot	permitted: up to 15 mm	permitted: up to 35 mm	permitted
Pinkknots	permitted	permitted	permitted
Filling	permitted	permitted	permitted
Slight cracks / hairline cracks	not permitted	permitted: up to 2x200 mm	permitted
Sugar inclusions, mineral inclusions	-	-	-
Bark pocket	not permitted	not permitted	not permitted
Lightning cracks	permitted: in knots	permitted: in knots	permitted
Slope of grain	no criterion	no criterion	no criterion
Healthy heart	not permitted	not permitted	permitted
Medullary ray	permitted	permitted	permitted
Discoloration, colour variation	permitted: bright to middle colours	permitted: bright colours	permitted: all colours
White streaks	-	-	permitted
Pilling sticks marking	not permitted	not permitted	not permitted
Biodeterioration (EN 1311)	not permitted	not permitted	not permitted
Non-visible parts			
All features without restrictions to size or quantity permitted, provided they do not affect the strength or durability of the floor.			
Comment			
Maximum 3% of floor board are allowed in the next lower grading. Wood is a natural product and therefore different in colour and texture. Samples, brochures and photos are therefore only approximate and not binding. The action of sunlight affects the natural variation in wood shade. This allows the product present at the time of delivery of significant differences to master.			

Changed:	QMB	File name:	20170116_PA_TDS_Parkett_Trendtime_Anhang_EN	
Date:	01.03.2013	Update:	www.parador.eu/service/catalogues-downloads/technical-data-sheets	
Our technical data sheets are constantly updated and adapted to the latest technology. This version replaces all earlier versions and is valid from:			16.01.2017	Page 3 of 4

Free sorting according to EN 13489					
Assortment:	Wide plank				
Characteristics according to EN 1310:	Upper side of the floor board				
Design:	Trendtime 9				
Type of wood:	Oak				
Botanical designation / Code (EN 13556):	Quercus petraea Liebl., Quercus robur L. / QCXE				
Origin:	DE, AT, HU, HR, SK, BA, UA, FR, CZ				
Shortcut / sorting / date (internal):	ER-L-FM-EI	ER-L-M-EI	ER-L-SB-EI	ER-L-HS-EI	ER-LH-WO-EI
	Version 1 2012	Version 1 2012	Version 1 2013	Version 6 2014	Version 3 2012
	Basket weave	Strip mix	Mini checkerboard pattern	Old Block pattern	Checkerboard
Grade:	Nature	Living	Nature	Living	Living
Sound sapwood	not permitted	not permitted	not permitted	permitted	not permitted
Knot (intergrown)	not permitted	permitted: up to 25 mm	not permitted	permitted: up to 30 mm	permitted: up to 25 mm
Falling out knot	not permitted	permitted: up to 15 mm	not permitted	permitted: up to 10 mm	permitted: up to 10 mm
Pinkknots	permitted: up to 2 mm	permitted: Cluster of knots	permitted: up to 5 mm	permitted	permitted: Cluster of knots
Filling	permitted	permitted	permitted	permitted	permitted
Slight cracks / hairline cracks	not permitted	not permitted	not permitted	permitted	permitted: in knots
Sugar inclusions, mineral inclusions	-	-	-	-	-
Bark pocket	not permitted	not permitted	not permitted	not permitted	permitted
Lightning cracks	not permitted	permitted	not permitted	-	-
Slope of grain	no criterion	no criterion	no criterion	no criterion	no criterion
Healthy heart	-	permitted	-	permitted	not permitted
Medullary ray	permitted	permitted	permitted	-	permitted
Discoloration, colour variation	permitted: slight colour variations	permitted	permitted: slight colour variations	permitted	permitted: slight colour variations
White streaks	-	permitted	permitted	permitted	-
Pilling sticks marking	not permitted	not permitted	not permitted	not permitted	not permitted
Biodeterioration (EN 1311)	not permitted	not permitted	not permitted	not permitted	not permitted
Non-visible parts					
All features without restrictions to size or quantity permitted, provided they do not affect the strength or durability of the floor.					
Comment					
Maximum 3% of floor board are allowed in the next lower grading. Wood is a natural product and therefore different in colour and texture. Samples, brochures and photos are therefore only approximate and not binding. The action of sunlight affects the natural variation in wood shade. This allows the product present at the time of delivery of significant differences to master.					

Changed:	QMB	File name:	20170116_PA_TDS_Parkett_Trendtime_Anhang_EN		
Date:	01.03.2013	Update:	www.parador.eu/service/catalogues-downloads/technical-data-sheets		
Our technical data sheets are constantly updated and adapted to the latest technology. This version replaces all earlier versions and is valid from:			16.01.2017	Page 4 of 4	